

ZIBO JINGGAN REFRACTORY IMPORT AND EXPORT CO.,LTD

Address:NO. 3, Yanhe Road, Boshan, Zibo, Shandong, China
Email:wp@cnjingganrefractory.com/sdwenping@163.com
Contact:Rose Tel/Wechat:+86-13275332819
Tel:86-533-4188518 Fax:86-533-4188518

Andalusite Runner Brick



1, Main performance parameters of Andalusite Runner Brick

ITEM	UNIT	CH-60	CH-70
Al ₂ O ₃	%	≥60	≥70
Andalusite content	%	15~20	18~30
Refractoriness	°C	1790	1790
Porosity	%	23~26	23~26
Density	g/cm ³	2.35~2.42	2.40~2.50
Compressive strength	Mpa	≥45	≥45
Refractoriness under load	°C	≥1450	≥1500
Linear change rate 1450°C*2h	%	0.1~-0.3	0.1~-0.3
Thermal shock stability 950°C,air cooling,	times	>25	>30

2. Brief introduction: Andalusite Runner Brick is made of Calcined Bauxite as the main raw material, added with imported andalusite powder from South Africa, and fired at 1400 °C - ~ 1450 °C. Andalusite Runner Brick has good thermal shock resistance and stability, and its application effect is greatly superior to clay and high aluminum products. It is better than clay and high aluminum products in terms of erosion resistance and erosion resistance of molten steel and molten iron, which is very popular with users

3. Characteristics of Andalusite Runner Brick:

- 1) Good thermal shock resistance and stability, greatly superior to clay and high aluminum products
- 2) Good high temperature stability

ZIBO JINGGAN REFRACTORY IMPORT AND EXPORT CO.,LTD

- 3) The application effect is far better than clay and high aluminum products
4. Application: suitable for flowing casting process of molten steel and iron in steel plant and foundry
5. Good feedback of product use effect, the products have been exported to South Korea, Japan, Pakistan
6. We are a professional supplier, who can provide customers with free product technology, use and other issues.

Do you want to find a professional supplier of refractory products?

Do you want to find a professional supplier of graphite electrodes?

Do you want to find a stable and credible supplier?

Then let's contact with jinggan company

Contact me:

Email: wp@cnjingganrefractory.com / sdwenping@163.com

TEL: 86-0533-4188518 / **FAX:** 86-0533-4188518

Rose: +86-13275332819 (wechat/whatsapp number)